

TENDITALIA
i feel at home

Ed. 8 – 23/04/2024

Vanity Up

Visual comfort



2370 mm ca. ↔



Visual comfort



Hi tech



Trend & design



Architectural fabrics



700




235



145



042



331



131



025



043



330



300



020



022



000



001



023



010

Dati tecnici	Technical details	Technisches Datenblatt	Standard
Altezza tessuto	Fabric height	Breit	2370 mm
Composizione	Fabric description	Materialbeschreibung	100% Poliestere 100% Polyester 100% Polyester
Resinatura	Coating	Beschichtung	100% Resina poliestere 100% Resins poliester 100% Beschichtung polyester
Peso tessuto	Fabric weight	Gewebegewicht	70±5 (g/m ²)
Peso rivestimento	Coating weight	Beschichtungsgewicht	12±5 (g/m ²)
Peso totale	Total weight	Gesamtgewicht	82±10 (g/m ²)
Spessore	Thickness	Stoffdicke	0.15±0.05 mm
Comportamento alla fiamma	Flame resistance	Flammhemmung	Non ignifugo Flammable entflammbar
Comportamento da appeso (rullo)	Hanging behaviour (roller) (MA34)*	Hängeverhalten (Rollos)	(%) < 2.0
Stabilità dimensionale (6h, 80°C)	Dimensional stability	Maßbeständigkeit	Trama (Weft, Schuß) <1 (%) Ordito (Warp- Kette) <1 (%)
Manutenzione	Maintenance	Pflege- und Reinigungshinweise	Pulire con panno umido Cleaning with a damp cloth Bedingt Feucht abwischbar
Prodotto privo di formaldeide	Formaldehyde Free	Ohne Formaldehyde	No No Nein
Esente da PVC e alogeni	PVC and halogen Free	PVC – und halogenfrei	Si Yes Ja
Protezione da muffe e batteri (trattamento Hygienguard)	Guarantees product resistance to attacks and insurgence of bacteria and moulds	Optimaler Schutz in Feuchträumen – fungizid und bakteristatisch	No No Nein
Conformità REACH	REACH Compliant	REACH-Verordnung	Si Yes Ja
Valori energetici	Energetic value	Energetische Werte	Standard
Stabilità alla luce	Light fastness	Lichtechtheit	≥ 5/6 (DIN EN ISO 105 B02)

* MA: metodo di analisi interno Tenditalia

* MA: TENDITALIA'S internal method analysis

* MA: Tenditalia interne Prüfmethode

G-tot*
(EN 14501)

Color	± 0.01	020	022	023	025	145	042	043	001	010	131	700	331	330	000	300	235
G-tot		0.51	0.51	0.51	0.55	0.55	0.55	0.51	0.49	0.51	0.55	0.55	0.55	0.55	0.49	0.51	0.55

** valore "g tot" calcolato considerando: doppio vetro tipo C (EN14501) con copertura termoprotettiva e spazio riempito con Argon (U: 1.2 W/m2K e g: 0.59) e tende chiuse
** g tot" value calculated considering: Double-glazing, low emissivity coating, space filled with Argon, Glass Type C (U: 1.2 W/m2K and g: 0.59) and closed curtains
** wert "g tot" berechnet Doppelverglasung mit thermoreflektierender Beschichtung, Zwischerraum mit Argon gefüllt (U: 1.2 W/m2 K und g 0.59) bei geschlossenem Lamellenvorhang

Comportamento alla luce Behaviour to the light Lichtreflektion
(EN 410)

Color	± 2%	020	022	023	025	145	042	043	001
Riflessione luce / light reflection / Reflektion		38	40	38	12	11	13	40	45
Trasmissione / light transmission / Transmission		40	42	38	17	15	12	32	50
Assorbimento / light absorption / Absorption		22	18	24	71	74	75	28	5

	010	131	700	331	330	000	300	235
Riflessione luce / light reflection / Reflektion	40	16	6	14	17	45	40	9
Trasmissione / light transmission / Transmission	46	13	5	9	11	50	32	6
Assorbimento / light absorption / Absorption	14	71	89	77	72	5	28	85

Classificazione di schermatura Performance classes Leistungsklasse
(EN 14501)

	020	022	023	025	145	042	043	001
Controllo del bagliore/Glare controle/Blendschutz	0	0	0	0	1	0	0	0
Privacy notturna/Night privacy/Sichtschutz bei Nacht	0	0	0	0	1	0	0	0
Contatto visivo con l'esterno/ Visual contact with outside/Durchsicht	1	2	1	1	0	1	1	2
Utilizzazione luce diurna/ Daylight utilisation/Tageslichtnutzung	2	4	2	2	1	2	2	4
Trasmissione energetica/ Heat protection/ sommerlicher Wärmeschutz***	0	0	0	0	0	0	0	1

	010	131	700	331	330	000	300	235
Controllo del bagliore/Glare controle/Blendschutz	0	0	1	1	1	0	0	1
Privacy notturna/Night privacy/Sichtschutz bei Nacht	0	0	1	1	1	0	0	1
Contatto visivo con l'esterno/ Visual contact with outside/Durchsicht	2	1	0	0	0	2	1	0
Utilizzazione luce diurna/ Daylight utilisation/Tageslichtnutzung	4	2	1	1	1	4	2	1
Trasmissione energetica/ Heat protection/ sommerlicher Wärmeschutz***	0	0	0	0	0	1	0	0

*** vetro C (iso 14501) U= 1,2 g= 0,59
*** glass C (iso 14501) U= 1,2 g=0,59
*** verglasung C (iso 14501) U=1,2 g=0,59